

ADiNO[®] FG 4755.0

Solvent-Based Foam Glue

Application

- Assembly bonding of upholstery PU foam material to itself, to fabrics, leather, wood, wood-based boards, plastics, metal, hardboard, paper-board, rubberized hair, fleece and other plasticizer free materials.
- Typically used in the mattress & upholstery industry.
- Medium-high tension bonding.

Characteristics

- Super high solid content.
- Very low consumption, low odour, low VOC emissions.
- One-side application.
- Soft glue-line.
- Good sprayability using rotary spray nozzle.
- Due to very low solvent content, no ignition from electrostatic discharges in metallic spring mattresses.

Technical Data

Basis		: Synthetic Polymer
Colour		: .0 = beige, .5 = red
Solid content		: approx. 75 %
Viscosity @ 30°C	(Brookfield)	: approx. 2,500 mPa.s
Density		: approx. 0.94 g/cm ³
Application quantity	(depending on materials used)	: 55-70 g/m ² in one-side application : 30-35 g/m ² per side in two-side application
Open time	(Adino test method)	: approx. 7 minutes in one-side application : approx. 10 minutes in two-side application

Instruction for Use

Apply the adhesive from flow-cup, pressure tank, or pump system, nozzle in size 1.5-2.0mm, material pressure 2-5 bar. One-side application and immediate joining. For higher tension, let the adhesive evaporate for a few seconds and join with higher force, or use two-side application.

Factors such as temperature, humidity, substrate and application quantity influence the open time / tackiness and setting time; increased temperatures shorten the open and setting time. Self-tests are required to determine precise required processing parameters.

Don't use for Polystyrene-foam (PS).

To clean the used equipment or in case of long-term work stops use ADiNO[®] CL 4970.0 also suitable to dilute ADiNO[®] FG 4755.0

Packaging / Storage

170 kg steel drum, smaller units on request / shelf-life 12 months after production date in tightly sealed container
Keep in a cool and dry place

All information based on internal tests and many years of practical experience.

The variety of materials used and different work conditions, which lie beyond our control, preclude any claims based on this data. We recommend performing sufficient test and pilot run that our technical service team gladly support.

May 2025, Adino GmbH. Email: info@adinoklebstoffe.de – www.adinoklebstoffe.de
Eysseneckstraße 4, 60322 Frankfurt/Main, Germany