Technical Product Information

ADiNO® H 1105.0

Hardener

Application

- Increase of water resistance and increased adhesion when mixed in EPI-system adhesives

Technical Data			
Basis		:	Modified Polyisocyanate
Appearance		:	Liquid
Colour		:	Brown
Viscosity @ 30°C	(Brookfield)	:	approx. 300 mPa.s
Density		:	approx. 1.25 g/cm³
NCO content		:	approx. 31%

Instruction for Use

Mix 7 – 15 % ppw H 1105.0 hardener into the adhesive and stir well, it must be mixed with proper mixing equipment for a minimum of 2–3 minutes to achieve a uniform and homogeneous dispersion.
Processing time (pot life) 30 – 60 minutes, depending on hardener dosage and type of dispersion adhesive.

Packaging / Storage

5 kg bottle / shelf-life 12 months after production date.
Keep in a cool and dry place

All information based on internal tests and many years of practical experience.
The variety of materials used and different work conditions, which lie beyond our control, preclude any claims based on this data.
We recommend performing sufficient test and pilot run that our technical service team gladly support.

October 2026, Adino GmbH. *Email: info@adinoklebstoffe.de – www.adinoklebstoffe.de*
Eysseneckstraße 4, 60322 Frankfurt/Main, Germany